



10-3008

FLEXIBLE STRUCTURAL EPOXY ADHESIVE

DESCRIPTION:

10-3008 is a filled, high performance structural epoxy adhesive. 10-3008 is a flexible adhesive with outstanding lap shear and peel strength. It is a great choice for bonding substrates of differing coefficients of thermal expansion. 10-3008 is also an excellent adhesive for applications requiring impact and vibration resistance.

10-3008 has a convenient 1:1 by volume mix ratio and therefore is ideal for Dual Barrel Cartridge packaging. 10-3008 is stocked in 50ML and 200ML Dual Cartridge sizes.

10-3008 contains non-abrasive fillers and therefore is well suited for meter mix and dispense equipment.

FEATURES:


- * 1:1 Non-critical mix ratio
- * Thermal shock resistance
- * High lap shear strength
- * Excellent chemical resistance

TYPICAL SPECIFICATIONS:

Color, Resin	Grey
Catalyst	Beige
Viscosity, 25°C, cps Resin	650,000
Catalyst	77,867
Mixed	96,000
Mix ratio, by volume (Resin:Catalyst)	1:1
by weight (Resin:Catalyst)	1:1.3
Specific gravity, 25°C Resin	1.69
Catalyst	1.23
Pot life, 100 gram mass, 25°C	60 Minutes
Hardness, shore D	55-65

1-800-EPOXIES (376-9437) • 401-946-5564 • Fax: 401-946-5526

21 Starline Way • Cranston, RI 02921 USA
www.epoxies.com • service@epoxies.com



Epoxy, Urethane & Silicone Formulations

Lap shear strength (AL/AL), psi

7 days room temp. cure	2,900
18 hours + 2 hours @ 212°F	3,000
1 hour @ 180°F	3,000
2 hours @ 150°F	3,200
30 minutes @ 250°F	2,700

T-Peel strength, piw

7 days room temp. cure	25
18 hours + 2 hours @ 212°F	25
1 hour @ 180°F	23
2 hours @ 150°F	26
30 minutes @ 250°F	23

INSTRUCTIONS FOR USE:

- 1) Stir Resin and Catalyst separately in their original containers.
- 2) By volume, thoroughly mix equal parts Resin and Catalyst. Be sure to scrape the sides and bottom of the mixing container.
- 3) Apply adhesive and follow one of the following cure schedules:

Room Temperature	18-24 Hours
150°F	2 Hours
180°F	1 Hour
250°F	30 Minutes

STORAGE, HANDLING AND AVAILABILITY:

Store in a cool, dry place in original containers. Keep containers closed and stir well before using.

Expected shelf life is 1 year in original unopened container.

10-3008 is available in 50ML and 200ML Dual Barrel Cartridges, Quarts, Gallons, 5 Gallon Pails, and 55 Gallon Drums.

1-800-EPOXIES (376-9437) • 401-946-5564 • Fax: 401-946-5526

21 Starline Way • Cranston, RI 02921 USA
www.epoxies.com • service@epoxies.com



IMPORTANT:

The information in this brochure is based on data obtained by our research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/03

1-800-EPOXIES (376-9437) • 401-946-5564 • Fax: 401-946-5526

21 Starline Way • Cranston, RI 02921 USA

www.epoxies.com • service@epoxies.com