

20-1615

WATER CLEAR SILICONE POTTING COMPOUND

DESCRIPTION:

20-1615 is a two component, room temperature curing silicone rubber compound. This silicone system is clear, odorless, and low in viscosity. 20-1615 is an excellent choice for potting electronic assemblies that require shock and vibration resistance. It also protects assemblies from moisture, ozone, chemicals and other environmental hazards.

FEATURES:


- *Low viscosity
- *Contains no solvents
- *Operating temperature -115 to +205°C
- *No exotherm during cure
- *Hydrolytic stability
- *Easy 10:1 Ratio

TYPICAL SPECIFICATIONS:

Color	Water clear
Viscosity, 25°C, cps, mixed	6,000
Specific gravity, 25°C	1.03
Pot life @ 25°C	4 hours
Hardness, shore A	40
Tensile strength, psi	950
Elongation, %	120
Shrinkage, %	0.2
Refractive index	1.4
Dielectric strength, volts/mil	500
Dielectric constant @ 1000 Hz	2.7
Dissipation factor @ 1000 Hz	.0004
Volume resistivity, ohm-cm	1.2 x 10 ¹⁵
Operating temperature, °C	-115 to +205°C
Thermal conductivity, btu/hr, ft ² , °F/ft	0.12
Coefficient of expansion, in/in °F	18.3 x 10 ⁻⁵

1-800-EPOXIES (376-9437) • 401-946-5564 • Fax: 401-946-5526

21 Starline Way • Cranston, RI 02921 USA
www.epoxies.com • service@epoxies.com



Epoxy, Urethane & Silicone Formulations

INSTRUCTIONS FOR USE:

- 1) By weight mix 100 parts 20-1615A Resin to 10 parts 20-1615B Catalyst.
- 2) Mix thoroughly and uniformly. Be careful not to whip excess air into mixture.
- 3) Degas if necessary to remove air from mixture. Select a mixing container 4-5 times larger than the volume of silicone material. Pull a vacuum of about 25mm (29 in.) of mercury. The silicone material will rise and then recede to the original level as the air bubbles break.
- 4) Pour and follow one of the cure schedules:

25°C	24-48 hours
65°C	4 hours
100°C	1 hour
125°C	45 minutes
150°C	10-15 minutes

Silicone rubber compounds will cure in contact with most clean, dry surfaces. Certain materials, such as butyl and chlorinated rubber, sulfur, amines and certain metal soap-cured silicone compounds can cause cure inhibition.

For improved adhesion contact Epoxies, Etc... Technical Department for the recommendation of a primer.

IMPORTANT:

The information in this brochure is based on data obtained by our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results to be obtained from the use thereof or that any such use will not infringe any patent. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/03

1-800-EPOXIES (376-9437) • 401-946-5564 • Fax: 401-946-5526

21 Starline Way • Cranston, RI 02921 USA

www.epoxies.com • service@epoxies.com