

POLYURETHANE POTTING & ENCAPSULATING RESINS

THE GREEN SERIES

20-2101 Enterable Gel

20-2130 Shore A 30

20-2160 Shore A 60

20-2180 Shore A 80

DESCRIPTION:

This series of polyurethane systems is engineered for electronic potting, encapsulating, and casting applications. They are low in viscosity, low in toxicity and available in the popular TriggerBond® dual barrel cartridge dispensing system. These elastomeric systems are suitable for a variety of electronic insulating applications. The durometers range from an enterable gel to Shore A 80.

GREEN:

The base Natural Oil Polyol (NOP) used in these systems is obtained directly from a plant source without chemical modifications. Due to the raw materials selected, these products are **low in toxicity** and considered **GREEN** potting compounds. Using renewable resources, such as NOP's, will reduce the demand on non-renewable fossil fuels and reduce the overall production of carbon dioxide.

FEATURES:

- *Green
- *Low Viscosity
- *Available in TriggerBond
- *Low Durometer
- *Moisture Resistant
- *Convenient Mix Ratios
- *Low Shrinkage & Exotherm

BENEFITS:

- Reduce demand on non-renewable fossil fuels
- Quick self leveling around components
- Easy to use packaging
- Low stress on components & vibration resistant
- Can be used in wet environments
- Easy to process by hand or with meter mix
- Will not damage components during cure

TYPICAL PROPERTIES:

	<u>20-2101</u>	<u>20-2130</u>	<u>20-2160</u>	<u>20-2180</u>
Color	Clear	Green *	Green *	Green *
*Also available in Black				
Viscosity, 25°C, cps				
Polyol Resin	1,500	4,500	1,500	2,200
Isocyanate	2,000	1,700	5,500	1,500
Mixed	1,600	3,700	2,500	1,700
Specific gravity @ 25°C Resin				
Polyol Resin	0.968	0.971	1.03	0.972
Isocyanate	1.146	1.16	1.13	1.15
Mix Ratio (Iso:Polyol)				
By Volume	1:4	1:4	1:2	1:2
By Weight	25:100	25:100	55:100	60:100
Gel Time, 25°C				
Minutes	20	20	20	20
Elongation,	na	125	150	220
Tensile strength, PSI	na	150	375	1700
Tear strength, PLI	na	20	40	80
Coefficient of thermal expansion, °C	2.00 x10-4	2.00x10-4	2.00x10-4	2.10x10-4
Thermal conductivity,				
BTU/hr/ft2/°F/in	2.06	2.06	2.06	2.06
Operating temperature range, °C	-30 to +125	-30 to +125	-30 to +125	-30 to +125
Dielectric strength, volts/mil	625	625	625	650
Volume resistivity, ohm-cm	7.2x10 ¹⁴	7.2x10 ¹⁴	7.2x10 ¹⁴	7.2x10 ¹⁴
Surface resistivity, 25°C, ohm	>1.0x10 ¹⁵	>1.0x10 ¹⁵	>1.0x10 ¹⁵	>1.0x10 ¹⁵
Dielectric constant @1 KHz	4.0	3.6	3.6	3.4
Dissipation Factor @ 1 KHz	.017	.017	.017	.017

Note: When cured at room temperature full hardness and final properties are achieved in 7-10 days.

INSTRUCTIONS FOR USE:

1. By weight, thoroughly mix according to mix ratio provided in the above table. Two components should be carefully weighed in metal, plastic or glass containers. Avoid using paper cups and wooden stirrers. Weighing & mixing is not necessary when using TriggerBond® cartridges.
2. Mixed material can be degassed at 1 to 5 mm Hg to ensure bubble free castings. Containers should be large enough to allow frothing.
3. Cure according to one of the following cure schedules:
 25°C 24 Hours
 45°C 2.5 Hours
 65°C 1.5 Hours
 85°C 40 Minutes



STORAGE & HANDLING & SAFETY:

Store both components at 75-85°F in original containers. If the containers are opened and the contents partially used, the material left in the container should be blanketed with dry nitrogen before sealing. Carefully read Material Safety Data Sheets before using.

AVAILABILITY:

These products are available in the convenient TriggerBond® dual barrel cartridges (50ml, 200ml & 400ml), quarts, gallons, five gallon pails and 55 gallon drums.

IMPORTANT:

The information in this brochure is based on data obtained by our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

09/09